

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
31 July 2003 (31.07.2003)

PCT

(10) International Publication Number
WO 03/062666 A1

(51) International Patent Classification⁷: **F16G 5/20**

(21) International Application Number: **PCT/US03/01238**

(22) International Filing Date: **13 January 2003 (13.01.2003)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(30) Priority Data:
60/349,795 **16 January 2002 (16.01.2002)** **US**

(71) Applicant: **THE GATES CORPORATION [US/US];**
900 South Broadway, Denver, CO 80209 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR).

Published:


— *with international search report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(72) Inventor: **CHENG, Jiangtian;** 60 Villagecircle Dr.#15, Rochester Hills, MI 48307 (US).

(74) Agent: **THURNAU, Jeffrey;** The gates Corporation, Mail Stop: 31-4-1-A3, 900 So. Broadway, Denver, CO 80209 (US).

(54) Title: **MULTI-RIBBED BELT WITH TIP PROFILE**



(57) Abstract: The invention comprises a multi-ribbed belt (100) wherein rib tip (32) has a concave arcuate surface (36) disposed between substantially flat surfaces (41,42), which are in turn disposed between rib side surfaces (34,35). The substantially flat surfaces are adjacent to curved surfaces (39,40), which connect to rib side surfaces (34,35). The inventive rib profile and rib compound construction significantly reduce rib tip cracking, which significantly reduces belt flex fatigue under high applied frictional torque. Further, the inventive rib profile and rib compound construction significantly reduces high localized tensile stress/strain at the rib tip and highly localized shear stress at the rib flank, thereby significantly reducing rib tip cracking and rib tear off. The inventive belt also comprises a significantly reduced contact normal force, thereby increasing an operating life of the belt.

What is needed is a multi-ribbed belt having improved belt flex fatigue. What is needed is a multi-ribbed belt having improved flex fatigue under a high frictional torque. What is needed is a multi-ribbed belt having a rib tip profile to minimize rib tip cracking. What is needed is a multi-ribbed belt having a rib tip profile to minimize rib/pulley interface contact deformation. What is needed is a multi-ribbed belt having a rib tip comprising a concave surface disposed on a flat surface between rib side surfaces. What is needed is a multi-ribbed belt having a reduced contact normal force. The present invention meets these needs.

Summary of the Invention

15 The primary aspect of the invention is to provide a multi-ribbed belt having improved belt flex fatigue.

Another aspect of the invention is to provide a multi-ribbed belt having improved flex fatigue under a high frictional torque.

20 Another aspect of the invention is to provide a multi-ribbed belt having a rib tip profile to minimize rib tip cracking.

Another aspect of the invention is to provide a multi-ribbed belt having a rib tip profile to minimize rib/pulley interface contact deformation.

25 Another aspect of the invention is to provide a multi-ribbed belt having a rib tip comprising a concave surface disposed on a flat surface between rib side surfaces.

Another aspect of the invention is to provide a multi-ribbed belt having a reduced contact normal force.

Fig. 4 is a cross-section of the inventive belt showing a contact normal force.

Detailed Description of the Preferred Embodiment

5 Fig. 1 is a plan end view of the inventive belt. The disclosed rib tip profile and rib construction minimizes rib tip cracking and rib/pulley interface contact deformation, and thus enhances belt flex fatigue strength in high torque applications. The inventive belt engages
10 two or more grooved pulleys. A torque is transmitted from a driver pulley to a driven pulley by a frictional contact between a belt ribbed surface and a pulley grooved surface.

The inventive belt 100 comprises overcord layer 10, tensile cords 20, undercord 30, and ribs 31.

15 Nylon short fiber reinforced fabric is used for the overcord layer 10. Other fabrics which may be used for overcord layer 10 include nylon and polyester woven fabric. An overcord thickness is in the range of approximately 0.40mm to 0.55mm.

20 Tensile cords 20 may comprise a high modulus cord, such as aramid cords having a cord diameter of approximately 0.65mm to 0.80mm and cord spacing of approximately 22~26 epi. Cords 20 are embedded in an
25 adhesion gum 11 having a Young's modulus in the range of approximately 40 to 60Mpa. Cords 20 may also comprise polyester cord having a cord diameter in the range of approximately 0.85 to 0.94mm and cord spacing in the range of approximately 20 to 22 epi. Cords 20 are embedded in an
30 adhesion gum 11 with Young's modulus in the range of approximately 25 to 40Mpa. Other tensile cord materials also include aramid, polyester, nylon 4.6 or nylon 6.6 and

Curved surfaces 39 and 40 each describe a radius R2. Surfaces 39, 40 join substantially flat surfaces 41, 42 to rib flanks 34, 35 respectively. R2 is in the range of approximately 0.20mm to 0.75mm.

5 Curved surface 37 having radius R3 joins adjacent rib flanks 34, 35. Surface 37 has a radius in the range of approximately 0.15mm to 0.45mm.

The inventive rib profile and rib compound construction significantly reduce rib tip cracking, which
10 significantly reduces belt flex fatigue under high applied frictional torque. The compound comprises:

	Composition	Weight Parts
	Polymer (Rubber)	100
	Carbon black	5~30
15	Short Fiber (1~6mm)	3~8
	Silica	30~60
	Oil	10
	AOX	1
	CoAgent	15
20	Cure	6

Further, the inventive rib profile and rib compound construction significantly reduces high localized tensile stress/strain at the rib tip and highly localized shear stress at the rib flank, thereby significantly reducing rib
25 tip cracking and rib tear off. The smooth curved surfaces 39, 40 minimize concentrated contact deformation due to rib wedging into a pulley groove.

Fig. 2 is a graph showing a reduced rib tip tensile stress/strain for the inventive rib. In the inventive rib
30 construction, the rib tip surface 36 contributes to minimize a rib tip high tensile stress/strain during back bending on a flat pulley. The smooth curved surfaces 39,

Claims

I claim:

1. A belt comprising:

an elastomeric body having a tensile member
embedded therein and a pulley engaging surface;
the pulley engaging surface having a rib extending
in a longitudinal direction;
the rib having a tip describing a concave surface
disposed between substantially flat surfaces.

2. The belt as in claim 1 wherein the concave surface
further comprises an arcuate surface.

3. The belt as in claim 2 further comprising;
a first curved surface and a second curved surface
on either side of the substantially flat surfaces,
each joining the concave surface to a rib flank.

4. The belt as in claim 3 further comprising:
a third curved surface joining adjacent rib flanks;
and
an angle between adjacent rib flanks in the range
of approximately 34° to 46°.

5. The belt as in claim 3, wherein the first curved
surface and the second curved surface each have
substantially equal radii.

6. The belt as in claim 3 further comprising an
overcord disposed opposite a rib relative to the
tensile member.

1/2




FIG. 1




FIG. 2

INTERNATIONAL SEARCH REPORT

Inte Application No

PC1/US 03/01238

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 F16G5/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 F16G B29D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

PAJ, WPI Data, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 034 225 A (GATES RUBBER CO) 26 August 1981 (1981-08-26) page 8, line 11 - line 22; figures 10-13 ----	1
A	US 4 944 717 A (GEORGET PIERRE) 31 July 1990 (1990-07-31) cited in the application the whole document ----	1
A	US 5 492 507 A (KUMAZAKI TOSHIMI) 20 February 1996 (1996-02-20) cited in the application the whole document ----	1
A	US 2 054 619 A (FREEDLANDER ABRAHAM L) 15 September 1936 (1936-09-15) page 2, right-hand column, line 44 - line 49; figure 18 ----- -/-	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

7 May 2003

Date of mailing of the international search report

14/05/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Baron, C

INTERNATIONAL SEARCH REPORT

Intern Application No

PC1/US 03/01238

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
EP 0034225	A	26-08-1981	EP	0034225 A1	26-08-1981
			DE	3065966 D1	02-02-1984
US 4944717	A	31-07-1990	FR	2633687 A1	05-01-1990
			DE	68910742 D1	23-12-1993
			DE	68910742 T2	05-05-1994
			EP	0349434 A1	03-01-1990
			ES	2046507 T3	01-02-1994
			JP	2125123 A	14-05-1990
US 5492507	A	20-02-1996	JP	2562112 B2	11-12-1996
			JP	7027181 A	27-01-1995
			CA	2127500 A1	08-01-1995
			CA	2255407 A1	08-01-1995
			DE	69413462 D1	29-10-1998
			DE	69413462 T2	11-02-1999
			EP	0633408 A2	11-01-1995
			US	5595533 A	21-01-1997
US 2054619	A	15-09-1936	NONE		
US 2361645	A	31-10-1944	NONE		
US 2214098	A	10-09-1940	NONE		
EP 1167814	A	02-01-2002	JP	2003014052 A	15-01-2003
			CN	1348070 A	08-05-2002
			EP	1167814 A1	02-01-2002
			US	2002039947 A1	04-04-2002
US 4904232	A	27-02-1990	DE	3837892 A1	10-05-1990